ARdur® 1 side



Colourless



High level of hardness



Highly wear-resistant




Achromatic





Reflection curve



Properties Option

| optiou. | | |
|----------------|---|--|
| Reflection ≤3% | _ | |
| UV filter | _ | |
| Achromatic | • | |

Mechanical

| Hard | • |
|-----------------------|---|
| Highly wear-resistant | • |
| Anti-static | • |

Chemical

| Water- and oil-repellent | _ |
|--------------------------|---|
| Resistant to solvents | • |
| Low-temperature process | _ |
| Alkali-resistant | _ |
| Resistant to ultrasound | • |

Geometric

| | Drilling, opening | _ |
|--|-------------------|---|
| | Highly convex | • |

Product structure

| Sapphire | |
|------------|--|
| SCp ITO | |
| ITO | |

Quality tests

| Mechanical resistance | Description | Results |
|---|---|--------------|
| Vibratory finishing (chemical- mechanical polishing) | 2 hours in a vibrating bowl with cylindrical ceramic abrasives (Al2O3) | _ |
| Scratch-Test | Test to establish the hardness and adhesiveness of the coating using a diamond tip and variable loads | _ |
| Compliance with DIN-ISO 9211-4-02-02 | Rapid pull off testing (-1 s) using adhesive tape 12-13 mm wide. Adhesive strength > 9.8 N per 25 mm | Class 0 "OK" |

Chemical resistance

| "Thermal shock" test DIN-ISO 9211-4-04-12 | 3×2-minute cycles in de-mineralised water at 100 °C. 1 minute in de-mineralised water at room temperature | Class 0 "OK" |
|---|---|---------------------------------|
| Solubility DIN-ISO 9211-4-04-06 | 96 hours in a saline solution (45 g/l) at room temperature | _ |
| Solvent resistance DIN-ISO 9211-3-12-3 and 9022-87-04-1 | 1 h hour in acetone (CH ₃ COCH ₃) at room temper- ature | Class 0 "OK" |
| Resistance to ultrasound | Alkali bath (3% "Galvex") for 2 hours at 60 °C and 50 W of ultrasonic power | Class 1 "Minimal colour change" |
| Resistance to sweat DIN-ISO 9022-86-02-1 | 7 days in an artificial sweat solution | _ |

Resistance to climatic conditions

| Cold DIN-ISO 9022-10-09-1 | 16 hours at -55 °C | Class 0 "OK" |
|------------------------------|---|-----------------|
| Dry heat | 6 hours at 85 °C with relative humidity of <40% | Class 0 |
| DIN-ISO 9022-11-06-1 | | "OK" |

Cleaning instructions

Please observe the following instructions on how to clean glasses that have been treated with an anti-reflective coating: $\frac{1}{2} \int_{-\infty}^{\infty} \frac{1}{2} \left(\frac{1}{2} \int_{-\infty}^{\infty} \frac{1}{2} \left(\frac{$

- Glasses can be cleaned easily in a neutral solution using ultrasound and at temperatures of up to 60 $^{\circ}\text{C}.$
- If cleaning by hand, we recommend wearing single-use, powder-free latex gloves and using a lint-free cloth.
- Use one of the following approved cleaning alcohols: Ethanol with 5% isopropyl alcohol (F25-A+IPA), Alcosuisse, Bern Ethanol Absolute A 15 0 (02883), Sigma-Aldrich, Buchs SG

